

# LEDER &



# BIOTHANE®

## OLD - ANTIK



- **BOVINE HIDES**
- Origin: Extra European
- Average size: 4,00/4,20 m<sup>2</sup>
- Thickness: 1,0 mm +/-
- Natural grain
- Finishing in Aqueous solution
- **Always available in 13 colours**

Article with a natural grain and a characteristic aged effect, obtained with a particular working by through all the characteristics of the leather (wrinkles, scratches, insect bites, veins, etc.) are emphasized; they must be accepted and considered as signs of naturalness and not as defects.

**Application:** Contract, Public use, Hospitality, Residential.

**Fire resistant:** UNI EN 1021/1 – UNI EN 1021/2  
BS 5852 Source 0, 1  
FAR 25853 B  
BULLETIN 117 California Test

<b>Physical and colour fastness characteristics</b>		
<i>DRY RUBBING - 800 Cycles</i>	UNI EN ISO 11640	<i>Felt clean</i>
<i>WET RUBBING - 150 Cycles</i>	UNI EN ISO 11640	<i>Felt clean</i>
<i>FINISH ADHESION</i>	UNI EN ISO 11644	<i>&gt; 5 Newton/cm</i>
<i>FLEXING ENDURANCE - 30.000 Cycles</i>	UNI EN ISO 5402	<i>No surface damage or cracks</i>
<i>COLOUR FASTNESS TO LIGHT</i>	UNI EN ISO 105-B02	<i>&gt; 7 Blue scale</i>
<i>TEAR RESISTANCE</i>	UNI EN ISO 3377-1	<i>&gt; 20 Newton</i>

<b>Chemical characteristics</b>
<i>Chrome Tannage</i>
<i>Fatting as established by the Washington Convention</i>
<i>PCP (Pentachlorophenol), Hexavalent Chrome and Formaldehyde, as for the International law in force</i>
<i>Azo dyes absent</i>
<b>REACH</b> (Registration, Evaluation, Authorization and Restriction of Chemicals) ✓

WORRING LEDER GMBH – LAHNSTR. 30 – 45478 MÜLHEIM RUHR  
PHONE: 0208-52602 / FAX 0208-592071  
E-MAIL: INFO@WORRING-LEDER.DE / INTERNET: WWW.WORRING-LEDER.DE